

BESTENDIGHEID AFDICHTINGEN

MEDIUM	QUANTUM	QUANTUM								TOPGRAPH 2000	GRAFJET	TOPCHEM 2005	TOPCHEM 2006	TOPCHEM 2000/2003/ FTFE/SEALEX / SOFTCHEM/GORE
		ML1	C4400	C4430 PLUS	C4500	C4509	C8200	C4324						
A														
Aardgas	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Acetaldehyde	-	B	B	B	B	B	A	B	B	A	A	A	A	A
Acetamide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aceton	-	B	B	B	B	B	A	B	B	A	A	A	A	A
Acetyleen	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Adipinezuur	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluin	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminiumacetaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminiumchloraat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminiumchloride	A	A	A	A	A	B	A	A	A	A	A	A	A	A
Ammoniak	A	A	A	A	A	A	A	A	A	A	B	A	A	A
Ammoniumcarbonaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammoniumbicarbonaat	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammoniumchloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammoniumdifosfaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammoniumhydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Amylacetaat	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Aniline	-	C	C	C	C	C	C	C	C	A	A	A	A	A
Appelzuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Asfalt (teer)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
ASTM olie 1	-	A	A	A	A	A	A	A	A	A	A	A	A	A
ASTM olie 3	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Azijinether	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Azijnzuur	-	B	B	B	B	C	B	B	B	A	A	A	A	A
B														
Barciumchloride	-	A	A	A	A	A	A	A	-	A	A	A	A	A
Benzeen	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Benzine	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Benzoëzuur	-	B	B	B	A	B	A	B	B	A	A	A	A	A
Bleekmiddel	A	A	A	A	A	C	A	A	A	A	A	A	A	A
Boorzuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Borax	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Butaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Butanon (MEK)	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Butylacetaat	-	B	B	B	A	B	B	B	B	A	A	A	A	A
Butylalkohol (butanol)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Butylamine	-	C	C	C	C	C	C	C	C	C	A	A	A	A
C														
Calciumchloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Calciumhydroxide	A	A	A	A	A	B	A	A	A	A	B	A	A	A
Calciumhypochloriet	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Calciumsulfaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbolzuur (fenol)	-	C	C	C	C	C	C	C	C	-	A	A	A	A
Castor olie	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Chloor droog	-	A	A	A	A	A	A	A	A	B	A	A	A	A
Chloor nat	-	B	B	C	B	C	B	C	B	B	A	A	A	A
Chloorwater (0,5%)	-	A	A	A	A	C	A	A	A	B	A	A	A	A
Chloroform	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Chloromethaan	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Chroomzuur	-	B	B	B	B	C	B	C	C	C	A	A	A	A
Citroenzuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Clophen	A	A	A	A	A	A	B	A	A	A	A	A	A	A
Condensaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Creosoot	-	C	C	C	C	C	C	C	C	A	A	A	A	A
Cresol	-	B	B	B	B	B	B	B	B	A	A	A	A	A

Bestendigheidgraad: A = Geschikt | B = Toepasbaarheid is afhankelijk van de omstandigheden | C = Niet geschikt | - = Nooit onderzocht

BESTENDIGHEID AFDICHTINGEN

MEDIUM	QUANTUM									TOPGRAPH 2000	GRAFJET	TOPCHEM 2005	TOPCHEM 2006	TOPCHEM 2000/2003/ FTFE/SEALEX / SOFTCHEM/GORE
	ML1	C4400	C4430 PLUS	C4500	C4509	C8200	C4324							
Cyclohexanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cyclohexanon	-	C	C	C	C	C	C	C	C	C	A	A	A	A
D														
Dekaline	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Di-benzylether	-	C	C	C	C	C	C	C	C	C	A	A	A	A
Di-butylphthalaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Dieselolie	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Diethylether	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Dimenthyformamide	-	C	C	C	C	C	C	C	C	C	A	A	A	A
Diphyll (Dowtherm A)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
E														
Ethaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylacetaat	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Ethylalkohol (Ethanol)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylchloride	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Ethylidiamine	-	C	C	C	C	C	C	C	C	C	A	A	A	A
Ethyleen	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethleenchloride	-	C	C	C	C	C	A	C	C	C	A	A	A	A
Ethyleenglycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyleter	A	A	A	A	A	A	A	A	A	A	A	A	A	A
F														
Fenol	-	C	C	C	C	C	B	C	C	C	A	A	A	A
Fluorwaterstofzuur (10%)	-	C	C	C	C	B	C	A	C	C	A	C	B	B
Fluorwaterstofzuur (40%)	-	C	C	C	C	C	C	C	C	C	A	C	B	B
Formaldehyde	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Formamide	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Fosforzuur	A	A	A	A	A	A	C	A	C	A	A	A	A	A
Freon 12	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 22	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 13B1	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 221	-	B	B	B	B	B	A	B	A	A	A	A	A	A
Freon 23	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 134A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 290	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 404a	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 407c	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 410a	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 502	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 507	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 600a	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 717	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon 747	-	A	A	A	A	A	A	A	A	A	A	A	A	A
G														
Glucose	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycerine	A	A	A	A	A	A	A	A	A	A	A	A	A	A
H														
Heptaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Hydraulische olie (mineraal)	A	A	A	A	A	B	A	A	A	A	A	A	A	A
Hydraulische olie (fosf. Ester)	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Hydraulische olie (glycol base)	A	A	A	A	A	B	A	A	A	A	A	A	A	A
Hydrazinehydraat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
I														
Iso octaan	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Isopropylalkohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
K														
Kalkwater	A	A	A	A	A	A	A	A	A	A	A	A	A	A

Bestendigheidgraad: A = Geschikt | B = Toepasbaarheid is afhankelijk van de omstandigheden | C = Niet geschikt | - = Nooit onderzocht

BESTENDIGHEID AFDICHTINGEN

MEDIUM	QUANTUM									TOPGRAPH 2000	GRAFJET	TOPCHEM 2005	TOPCHEM 2006	TOPCHEM 2000/2003/ FTF/SEALEX / SOFTCHEM/GORE
		ML1	C4400	C4430 PLUS	C4500	C4509	C8200	C4324						
Kaliumacetaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kaliumcarbonaat	A	A	A	A	A	A	A	A	A	A	B	A	A	A
Kaliumchloraat	A	A	A	A	A	C	A	A	A	A	B	A	A	A
kaliumchloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kaliumchroomsulfaat	A	A	A	A	A	B	A	A	A	A	A	A	A	A
Kaliumcyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kaliumdichromaat	A	A	A	A	A	B	A	A	A	B	A	A	A	A
Kaliumiodide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kaliumhydroxide	-	B	B	B	A	B	A	B	B	A	C	A	A	A
Kaliumhypochloride	A	A	A	A	A	C	A	B	A	A	A	A	A	A
Kaliumnitraat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kaliumpermangaat	A	A	A	A	A	A	A	A	B	B	A	A	A	A
Kerosine (petroleum)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ketelvoedingswater alkalisch	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kooldioxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kooldisulfide	-	C	C	C	B	C	C	C	B	A	A	A	A	A
Kooltetrachloride	-	B	B	B	B	B	C	B	B	A	A	A	A	A
Koperacetaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Kopersulfaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
L														
Lijnzaadolie	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Loodacetaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Loodarsenaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Lucht	A	A	A	A	A	A	A	A	A	A	A	A	A	A
M														
Magnesiumsulfaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Melkzuur (50%)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Metaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Methylalkohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Methylchloride	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Methyleenchloride	-	C	C	C	C	C	B	C	C	A	A	A	A	A
Methylethylketon	-	B	B	B	B	B	B	B	B	A	A	A	A	A
Mierenzuur 10%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Mierenzuur 85%	B	B	B	B	A	B	A	B	B	A	A	B	A	A
N														
Nafta	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumaluminaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumcarbonaat	-	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumbisulfiet	-	A	A	A	A	B	A	A	A	A	A	A	A	A
Natriumchloride	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumcyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumhydroxide	-	B	B	B	A	B	A	B	B	A	C	A	A	A
Natriumsilikaat (waterglas)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumsulfaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumsulfide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumwaterstofcarbonaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Natriumwaterstofsulfide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Nitrobenzeen	-	C	C	C	C	C	C	C	C	A	A	A	A	A
O														
Octaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Oleum (rokend zwavelzuur)	-	C	C	C	C	C	C	C	C	C	A	C	A	A
Oliezuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Oxaalzuur	-	B	B	B	B	B	A	B	B	A	A	A	A	A
P														
Palmitinezuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Pekel	A	A	A	A	A	A	A	A	A	A	A	A	A	A

Bestendigheidgraad: A = Geschikt | B = Toepasbaarheid is afhankelijk van de omstandigheden | C = Niet geschikt | - = Nooit onderzocht

BESTENDIGHEID AFDICHTINGEN

MEDIUM	QUANTUM									TOPGRAPH 2000	GRAFJET	TOPCHEM 2005	TOPCHEM 2006	TOPCHEM 2000/2003/ FTFE/SEALEX / SOFTCHEM/GORE
	ML1	C4400	C4430 PLUS	C4500	C4509	C8200	C4324							
Pentaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Perchloorethleen	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Petroleum	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Petroleumether	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Phtaalzuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
propaan	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Pyridine	-	C	C	C	C	C	C	C	C	C	A	A	A	A
R														
Raapzaadolie	A	A	A	A	A	A	A	A	A	A	A	A	A	A
S														
Salysilzuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Salpeterzuur (20%)	-	C	C	C	C	C	B	C	C	C	B	A	C	A
Salpeterzuur (96%)	-	C	C	C	C	C	C	C	C	C	C	A	C	A
Siliconen olie	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Skydrol 500	-	C	C	C	C	C	C	C	C	C	A	A	A	A
Soda	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Stoom	A	B	B	B	B	B	B	B	B	A	A	A	A	A
Stearinezuur	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Stikstof	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Suiker	A	A	A	A	A	A	A	A	A	A	A	A	A	A
T														
Teer (asfalt/bitumen)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Terpentine	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Tetrachloorethaan	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Tetraline	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Tolueen	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Transformatorolie	A	A	A	A	A	A	B	A	A	A	A	A	A	A
Trichloorethyleen	-	B	B	B	B	B	B	B	B	B	A	A	A	A
Trietanolamine	A	A	A	A	A	A	A	A	A	A	A	A	A	A
U														
Urea	A	A	A	A	A	A	A	A	A	A	A	A	A	A
V														
Vinylacetaat	A	A	A	A	A	A	A	A	A	A	A	A	A	A
W														
Water	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Waterglas	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Waterstof	A	A	A	A	A	B	A	A	A	A	A	A	A	A
Waterstofchloride (droog)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Waterstofperoxide (<6%w.w.)	-	A	A	A	A	C	A	A	A	A	A	A	A	A
X														
Xylol/Xyleen	A	A	A	A	A	A	B	A	A	A	A	A	A	A
Z														
Zeep	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zeewater	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zetmeel	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zout	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zoutzuur 20%	-	B	B	B	A	C	A	B	B	B	A	A	C	A
Zoutzuur 30%	-	C	C	C	B	C	A	C	C	C	A	A	C	A
Zuurstof	-	A	A	A	A	B	A	A	A	A	A	A	A	A
Zwavel dioxide	-	B	B	B	B	C	A	B	B	B	A	A	A	A
Zwavelzuur	C	C	C	C	B	C	A	C	C	C	B	A	C	A
Zwaveligzuur	B	B	B	B	A	B	A	B	B	A	A	B	A	A

Bestendigheidgraad: A = Geschikt | B = Toepasbaarheid is afhankelijk van de omstandigheden | C = Niet geschikt | - = Nooit onderzocht